

ALPHA ASSOCIATES, INC.

145 LEHIGH AVE CN2013 LAKEWOOD, N.J. 08701
Phone: (732) 634-5700 Fax: (732) 634-1430

ALPHA - MARITEX
STYLE 2025/9480-AMA-1S



DESCRIPTION

Alpha Style 2025/9480-AMA-1S is a lamination of fiberglass fabric and aluminum foil with a silicone wash coat to protect the exposed surface and prevent fabric fraying on the laminated edges. This composite is designed to withstand temperatures of 450 °F with short exposure limits to 500 °F.

APPLICATIONS

Automotive applications including insulation facings and radiant heat shields.

ADVANTAGES

High temperature resistance, reflects radiant heat, good corrosion resistance.

PROPERTY DATA *STYLE 2025/9480-AMA-1S*

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776-96	21.5 oz/sy \pm 2.2	731 g/m ² \pm 74.8
THICKNESS	ASTM-D-1777-96	0.030" \pm 0.003"	0.762 mm \pm .076 mm
TENSILE STRENGTH	ASTM-D-5035-95	Warp- 250 lbs/inch Fill- 200 lbs/inch	44.72 kg/cm 35.72 kg/cm
TEAR STRENGTH	ASTM-D-5587-96	Warp- 50 lbs Fill- 50 lbs	22.68 kg 22.68 kg
MULLEN BURST	ASTM-D-3786-87	550 psi	38.5 kg/cm ²
FLAME RESISTANCE	ASTM-D-4723 ID # 36*	Char Length 1 inch max. Afterglow 12 sec. max. Flameout 5 sec. max.	2.54 cm max. 12 sec. max. 5 sec. max.
BOND STRENGTH	ASTM-D-1876-95	30 minute immersion (brake fluid) Result = 0.6 lbs./ inch minimum	0.107 kg/cm
TEMPERATURE RESISTANCE	FED SPEC HHB-100B	-40 °F to +450 °F.	-40 °C to 232 °C
COLOR AND COATING		Aluminum Foil	
BASE FABRIC AND WEAVE		Fiberglass/Plain Weave	

* Reference Method FED STD 191/5903.1

DATA SHEET 13043

REV D

DATE: 3/8/07

* All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.