

ALPHA ASSOCIATES, INC.

145 LEHIGH AVENUE LAKEWOOD, N.J. 08701
Phone: (732) 634-5700 Fax: (732) 634-1430

ALPHA - WELD
STYLE 2150 WELDGARD
(PRELIMINARY)



DESCRIPTION

Alpha Style 2150 WELDGARD is made of 100% glass yarns and treated with a special acrylic orange coating. It is designed to help reduce lint and increase workability of cloth. Base fabric is designed to resist intermittent temperatures up to 1000 F.

APPLICATIONS

Safety Apparel, Gaskets, Blankets, Insulation for Piping, Curtains, Stress Relieving and Heat Shields.

PROPERTY DATA STYLE 2150 WELDGARD

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776	24 oz/sy +/- 10%	1.19 Kg/m ² ± 10%
THICKNESS	ASTM-D-1777	0.050" +/- 10%	.152 cm +/- 10%
TENSILE STRENGTH	ASTM-D-5035	Warp- 400 lbs min. Fill- 400 lbs min.	345.6 kg/cm 230 kg/cm
TEMPERATURE RESISTANCE		1000 °F (Base Fabric - Intermittent)	538° C
ABRASION RESISTANCE	ASTM-E-96-66A	1000 Cycles min.	
CONSTRUCTION		10 (W) x 8 (F)	
COLOR		Orange	

CHEMICAL RESISTANCE: resists most acids and alkalis, except Hydrofluoric and hot phosphoric acids. Unaffected by bleaches or solvents. Won't rot or mildew.

DATA SHEET 13724

REV A

DATE: 09/30/02

* All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.