


ALPHA ASSOCIATES, INC.

ALPHA - ALAFLEX (SCRIM BASE)
STYLE 2213 EAM

145 LEHIGH AVENUE LAKEWOOD, N.J. 08701
Phone: (732) 634-5700 Fax: (732) 634-1430



DESCRIPTION

Alpha Alaflex Style 2213 EAM is a four ply laminate made with a fiberglass scrim adhered with a flame retardant adhesive to an aluminum foil face and heat-sealable film backing both sides.

- 1) Films - Endalon; 0.8 mil, Polyester; 0.6 mil.
- 2) Base Fabric - Fiberglass 2 x 2 scrim
- 3) Adhesive - Flame retardant ; Thermo setting
- 4) Foil - Aluminum

ADVANTAGES

Heat - sealable, Excellent vapor barrier, Solvent - sealable

APPLICATIONS

Flex Duct liner, Insulation Board Facing

PROPERTY DATA *STYLE 2213 EAM*

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776	2.7 oz/sy \pm 10%	92 g/m ² \pm 10%
THICKNESS	ASTM-D-1777	0.006" \pm 0.001"	0.152 mm \pm .025 mm
TENSILE STRENGTH	ASTM-D-5035	Warp- 25 lbs/inch Fill- 25 lbs/inch	4.47 kg/cm 4.47 kg/cm
TEAR STRENGTH	ASTM-D-1424	Warp- 15.87 oz. Fill- 15.87 oz.	450 gms. 450 gms.
BEACH PUNCTURE	ASTM-D-781	80 units (21.2 in/lbs)	24.4 cm/kg
FLAME RESISTANCE	FED 191/5903.2	Char Length 4.5 inches max. Afterglow 0.5 sec. max. Flameout 0 sec.	11.43 cm max. 0.5 sec. max. 0 sec.
HEAT - SEALABLE		Tear Bond	
PERMEABILITY (MVTR)	ASTM-E-96	Result = .05 perms	
CORROSION RESISTANCE	FED SPEC HHB 100B	120 °F 95% RH 20 days Result = No Corrosion	49 °C
TEMPERATURE RESISTANCE	FED SPEC HHB-100B	Cold - 0 °F Hot - +265 °F	-18 °C to 129 °C

DATA SHEET 12708

REV B

DATE: 10/1/98

* All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.