

ALPHA ASSOCIATES, INC.

145 LEHIGH AVE CN2013 LAKEWOOD, N.J. 08701
Phone: (732) 634-5700 Fax: (732) 634-1430

ALPHA - MARITEX
STYLE 3101-2-SS



DESCRIPTION

Alpha Maritex Style 3101-2-SS is a fiberglass fabric impregnated with a specially formulated silicone rubber designed to meet the rigid requirements for use in nuclear reactors. This special high temperature, flame retardant silicone rubber provides greater life and improved resistance to abrasion, flexing, tearing, and puncture.

Alpha Maritex Style 3101-2-SS was specifically designed as a low cost, light duty product for preparing high temperature (+500 °F) removable pads, flange and valve covers.

ADVANTAGES

Aluminum color, Water and Oil resistant, Flame retardant, Chemical resistant, Very Low Smoke, Easily sewn - drapeable, Lightweight, Easy to handle.

APPLICATIONS

Removable Insulation Pads, Flange Covers, Welding Curtains, Safety Clothing, Equipment Covers, Expansion Joints.

PROPERTY DATA *STYLE 3101-2-SS*

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776-96	15.0 oz/sy \pm 10%	510 g/m ² \pm 10%
THICKNESS	ASTM-D-1777-96	0.014" \pm 0.001"	0.356 mm \pm .025 mm
TENSILE STRENGTH	ASTM-D-5035-95	Warp- 300 lbs./inch Fill- 225 lbs/inch	53.58 kg/cm 40.19 kg/cm
TEAR STRENGTH	ASTM-D-5587-96	Warp- 50 lbs. Fill- 50 lbs.	22.68 kg 22.68 kg
BURST STRENGTH	ASTM-D-3786-87	600 psi	42 kg/cm ²
FLAME RESISTANCE	FED 191/5903.2	Char Length 1/16 inch max.	0.159 cm max.
		Afterglow 1 second max.	1 second max.
		Flame Out 1 second max.	1 second max.
TEMPERATURE RESISTANCE	FED SPEC HHB-100B	Cold (-67 °F) Continuous 1000 hrs @ +500 °F - No Change Intermittent 100 hrs @ +700 °F - Weight Loss = 10%, Strength Loss = 50%	-55 °C to 260 °C
BASE FABRIC and WEAVE		Fiberglass/Satin Weave	
COLOR and COATING		Silver Silicone Rubber	

DATA SHEET 12978

REV B

DATE: 10/1/98

* All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.