

ALPHA ASSOCIATES, INC.

145 LEHIGH AVE CN2013 LAKEWOOD, N.J. 08701
Phone: (732) 634-5700 Fax: (732) 634-1430

ALPHA - MARITEX
STYLE 3243 - M&A



DESCRIPTION

Alpha style 3243-M&A is a lamination of Alpha's Style 4348-AMAU and Navy hullboard fabric. The 4348-AMAU is a triple layer of lamination of aluminum foil, fiberglass scrim and a special metallized polyester film. The navy hullboard meets MIL-C-20079 Type I Class 2.

APPLICATIONS

Alpha Style 3243-M&A is designed as a facing material for mineral fiber and polyimide foam hull and pipe insulation in below ambient applications.

ADVANTAGES

This extremely tough jacketing and facing material provides abuse resistance and vapor retardation for applications where the insulation is exposed to physical and mechanical damage.

PROPERTY DATA

STYLE 3243 - M&A

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776-96	16.8 oz/sy \pm 10%	571.2 g/m ² \pm 10%
THICKNESS	ASTM-D-1777-96	0.02" \pm 10%	0.508 mm \pm 10%
TENSILE STRENGTH	ASTM-D-5035-95	Warp- 240 lbs./inch Fill- 180 lbs/ nch	42.86 kg/cm 32.15 kg/cm
TEAR STRENGTH	ASTM-D-5587-96	Warp- 40 lbs. Fill- 29 lbs.	18.14 kg 13.15 kg
BEACH PUNCTURE	ASTM-D-781-68	1300 units (344.5 in/lbs)	396.5 cm/kg
FLAME RESISTANCE	FED 191/5903.2	Char Length 0.25 " max. Afterglow 1 sec. max. Flame Out 1 sec. max.	0.635 cm max. 1 sec. max. 1 sec. max.
PERMEABILITY (MVTR)	ASTM-E-96-94	Result = 0.02 Permss	
CORROSION RESISTANCE	FED SPEC HHB 100B	120 °F 95% RH 20 days Result = No Corrosion	49 °C
TEMPERATURE RESISTANCE	FED SPEC HHB-100B	-40 °F to +200 °F	-40 °C to 93 °C
HEAT SEALABLE		Above 200 °F	93 °C

DATA SHEET 13184

REV C

DATE: 9/21/04

* All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.