


ALPHA ASSOCIATES, INC.

145 LEHIGH AVE CN2013 LAKEWOOD, N.J. 08701
Phone: (732) 634-5700 Fax: (732) 634-1430

ALPHA - MARITEX
STYLE 3259-2-SS



DESCRIPTION

Alpha Maritex Style 3259-2-SS is a fiberglass fabric impregnated with a specially formulated silicone rubber; 25% total by weight. It is designed to meet the rigid requirements for use in nuclear reactors. This special high temperature, flame retardant silicone rubber provides greater life and improved resistance to abrasion, flexing, tear and puncture. This material meets UL 214 and/or NFPA-701. The fabric thread count is 48 x 32. This product is designed specifically for high temperature (500 °F) removable pads, flange and valve covers. This STANDARD DUTY product can be manufactured to meet the requirements of NRC Guide 1.36 and Military Specification MIL-I-24244.

ADVANTAGES

Aluminum color, water and oil resistant, flame retardant, low smoke, easily sewn, light weight.

APPLICATIONS

Removable Insulation Pads, Flange Covers, Welding Curtains, Safety Clothing, Equipment Covers, Expansion Joints.

PROPERTY DATA STYLE 3259-2-SS

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776-96	17.5 oz/sy \pm 10%	595 g/m ² \pm 10%
THICKNESS	ASTM-D-1777-96	0.018" \pm 0.001"	0.457 mm \pm .025 mm
TENSILE STRENGTH	ASTM-D-5035-95	Warp- 325 lbs/inch min. Fill- 250 lbs/inch min.	58.04 kg/cm 44.64 kg/cm
TEAR STRENGTH	ASTM-D-5587-96	Warp- 60 lbs min. Fill- 60 lbs min.	27.15 kg 27.15 kg
BURST STRENGTH	ASTM-D-3786-87	600 psi min.	63 kg/cm ²
FLAME RESISTANCE	FED 191/5903.2	Char Length 1/16" inch max. Afterglow 1 second max. Flame Out 1 second max.	1.54 cm max. 1 second max. 1 second max.
BASE FABRIC and WEAVE		Fiberglass/Satin Weave	
COLOR and COATING		Silver Silicone	

TEMPERATURE RESISTANCE- Cold: -67 °F (-55 °C)
Hot: Continuous 1000 hrs. @ +500 °F (260 °C) = no change
Intermittent 100 hrs. @ +700 °F (371 °C) Weight loss=10%, Strength loss=50%

DATA SHEET 12449 REV G DATE: 5/10/07 * All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.