

# ALPHA ASSOCIATES, INC.

ALPHA - ALAFLEX (SCRIM BASE)  
STYLE 5515 MA (HW)

145 LEHIGH AVE CN2013 LAKEWOOD, N.J. 08701  
Phone: (732) 634-5700 Fax: (732) 634-1430



## DESCRIPTION

Alpha Alaflex Style 5515-MA is a fiberglass fabric coated with a black elastomer (Neoprene) compound and laminated to an aluminized polyester film. This product is a U.L. listed sheathing material.

1. Base Fabric - Fiberglass 5 x 5
2. Coating - Neoprene - black (cured)
3. Film - Polyester 1/2 mil. aluminized

---

## *PROPERTY DATA*

### *STYLE 5515 MA (HW)*

---

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776-96	3.30 oz/sy $\pm$ 5 %	112.2 g/m <sup>2</sup> $\pm$ 5%
THICKNESS	ASTM-D-1777-96	0.010" $\pm$ 0.001"	0.254 mm $\pm$ .025 mm
TENSILE STRENGTH	ASTM-D-5035-95	Warp- 40 lbs./inch Fill- 35 lbs/inch	7.14 kg/cm 6.25 kg/cm
TEAR STRENGTH	ASTM-D-1424-96	Warp- 56.44 oz. Fill- 42.33 oz.	1600 gms. 1200 gms.
BEACH PUNCTURE	ASTM-D-781-68	100 units (26.5 in/lbs)	30.5 cm/kg
FLAME RESISTANCE	FED 191/5903.2	Char Length 2 inches max. Afterglow 1 second max. Flame Out 2 seconds max.	5.08 cm max. 1 second max. 2 seconds max.
PERMEABILITY (MVTR)	ASTM-E-96-94	Result - 0.1 Perms	
CORROSION RESISTANCE	FED SPEC HHB 100B	120 °F 95% RH 20 days Result = No Corrosion	49 °C
TEMPERATURE RESISTANCE	FED SPEC HHB-100B	Cold: -20 °F @ 24 hrs. (no delamination) Hot: +200 °F @ 24 hrs. (no delamination)	-29 °C to 93 °C

DATA SHEET 12856

REV B

DATE: 10/1/98

\* All values are nominal unless otherwise specified.

### **Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications**

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.