

# ALPHA ASSOCIATES, INC.

145 LEHIGH AVENUE LAKEWOOD, N.J. 08701  
Phone: (732) 634-5700 Fax: (732) 634-1430

ALPHA - ALAFLEX (SCRIM BASE)  
STYLE 59-M WHITE



## DESCRIPTION

Alpha Style 59-M White is a lamination of 100% fiberglass scrim and polyester film. It is laminated using a white, high temperature-resistant, fire-retardant adhesive.

## ADVANTAGES

- Resistant to oil and water
- Tough - resists damage and has excellent puncture resistance
- High tear strength
- White color eliminates need for painting
- Surface is paintable, if desired\*

## APPLICATIONS

Sound absorption membrane  
Facing for Navy hullboard

---

## PROPERTY DATA STYLE 59-M WHITE

---

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776	3.0 oz/sy $\pm$ 10%	102 g/m <sup>2</sup> $\pm$ 10%
THICKNESS	ASTM-D-1777	.008" nominal	0.203 mm nominal
TENSILE STRENGTH	ASTM-D-5035	Warp- 50 lbs/inch	8.93 kg/cm
		Fill- 50 lbs/inch	8.93 kg/cm
TEAR STRENGTH	ASTM-D-5587	Warp- 7 lbs	3.18 kg
		Fill- 7 lbs	3.18 kg
BEACH PUNCTURE	ASTM-D-781	400 units (106 in/lbs)	122 cm/kg
FLAME RESISTANCE	FED 191/5903.2	Char Length 5 1/2 inch max.	13.97 cm max.
		Afterglow 1 sec. max.	1 sec. max.
		Flame Out 1 sec. max.	1 sec. max.
PERMEABILITY (MVTR)	ASTM-E-96	Result - 0.5 Perms	
CORROSION RESISTANCE	FED SPEC HHB 100B	120 °F 95% RH 20 days Result - No Corrosion	49 °C

Complies to U.S. Coast Guard #46 - CFR 164.012 Interior Finish  
U.S. Coast Guard Certificate of Approval 164.012/73/0

\* Contact Alpha Associates' Technical Department for paint types.

DATA SHEET 13355

REV B

DATE: 10/1/98

\* All values are nominal unless otherwise specified.

### **Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications**

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.