

ALPHA ASSOCIATES, INC.

145 LEHIGH AVENUE LAKEWOOD, N.J. 08701
Phone: (732) 634-5700 Fax: (732) 634-1430

ALPHA
STYLE 7578-VS-2



DESCRIPTION

Style 7578-VS-2 is a medium weight vinyl coated fiberglass. Style 7578-VS-2 meets the requirements of UL 181, Class 1.

APPLICATIONS

This product is designed for use as a core material for flexible duct applications and can also be used as a facing material for sound attenuating blankets and many other applications.

PROPERTY DATA

STYLE 7578-VS-2

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776	6 oz/sy \pm 10%	204 g/m ² \pm 10%
THICKNESS	ASTM-D-1777	0.006" \pm 10%	0.152 mm \pm 10%
TENSILE STRENGTH	ASTM-D-5035	Warp- 125 lbs./in. Fill- 120 lbs/in.	22.33 kg/cm 21.43 kg/cm
TEAR STRENGTH	ASTM-D-1424	Warp- 52.91 oz. Fill- 59.96 oz.	1500 gms. 1700 gms.
MULLEN BURST	ASTM-D-3786	275 psi	19.25 kg/cm ²
FLAME RESISTANCE	FED 191/5903.2	Char Length 1 inch max.	2.54 cm max.
		Afterglow 1 sec. max.	1 sec. max.
		Flame Out 0 sec. max.	0 sec. max.
TEMPERATURE RESISTANCE	Operating Temperature	250 °F max. (continuous)	121 °C max.
ABRASION RESISTANCE	ASTM-D-3389	Wheel - H22 Load-500 g Revolutions - 250 End Point - Break in yarns	
COLOR		Silver	
APPEARANCE		No Pinholes	

DATA SHEET 12844

REV B

DATE: 3/25/99

* All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.