

# ALPHA ASSOCIATES, INC.

145 LEHIGH AVE CN2013 LAKEWOOD, N.J. 08701  
Phone: (732) 634-5700 Fax: (732) 634-1430

ALPHA - MARITEX  
STYLE 8451-S



## DESCRIPTION

Alpha Maritex Style 8451-S is a welding curtain material made with a fiberglass cloth base and a silicone rubber coating to meet the rigid requirements of the US Navy, specifically on nuclear submarines, and meets Spec. #5404-4, Revision C, dated 10 June 1976. It also meets Specification MIL-C-24576(SH) 25 July 1978, Type III Class 1. Alpha Maritex Style 8451-S meets the requirements of ASTM-E162 and this material is in compliance with the requirements of Section 5.302-3 of the Mandatory Safety Standards Underground Coal Mine.

## ADVANTAGES

The special fire-retardant silicone rubber provides greater life and improved resistance to abrasion, flexing, tear and puncture. This material passes all tests for toxic fumes and meets all of the Federal Standards and OSHA Specifications.

---

## PROPERTY DATA STYLE 8451-S

---

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776-96	30-36 oz/sy	1020 g/m <sup>2</sup> - 1220 g/m <sup>2</sup>
THICKNESS	ASTM-D-1777-96	.037" ± .002"	0.940 mm ± .05 mm
TENSILE STRENGTH	ASTM-D-5034-95	Warp- 375 lbs/inch Fill- 225 lbs/inch	66.98 kg/cm 40.19 kg/cm
TEAR STRENGTH	ASTM-D-5587-96	Warp- 35 lbs Fill- 35 lbs	15.88 kg 15.88 kg
BURST STRENGTH	ASTM-D-3786-87	600 psi	42 kg/cm <sup>2</sup>
FLAME RESISTANCE	FED 191/5903.2	Char Length 1 inch max. Afterglow 4 sec. max. Flame Out 5 sec. max.	2.54 cm max. 4 sec. max. 5 sec. max.
TEMPERATURE RESISTANCE	FED SPEC HHB 100B	-67 °F to 500 °F	-55 °C to 260 °C
BASE FABRIC and WEAVE		Fiberglass/Satin Weave	
COATING		Flame Retardant Silicone Rubber	
STIFFNESS	MIL-C-24576 (SH)	Warp- .1600 in/lbs max. Fill- .0800 in/lbs max.	

DATA SHEET 12784

REV B

DATE: 10/1/98

\* All values are nominal unless otherwise specified.

### Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.