

ALPHA ASSOCIATES, INC.

145 LEHIGH AVENUE LAKEWOOD, N.J. 08701
Phone: (732) 634-5700 Fax: (732) 634-1430

ALPHA - MARITEX
STYLE 8460-2-SS



DESCRIPTION

Alpha Maritex Style 8460-2-SS is a fiberglass fabric meeting Military Specification MIL-Y-1140C impregnated with a specially formulated silicone rubber designed to meet the rigid requirements for use in nuclear reactors. This product is designed specifically for high temperature (500 °F) removable pads, flange and valve covers. This (Heavy Duty) silicone impregnated fiberglass fabric is used where more wear and tear is needed.

ADVANTAGES

Aluminum color, Water and Oil resistant, Acid and Alkali resistant, Flame retardant, Low Smoke, Easily sewn, Adhesive bonded or sealed. The special high temperature, flame retardant silicone rubber provides greater life and improved resistance to abrasion, flexing, tear and puncture.

APPLICATIONS

Removable Insulation Pad Covering, Flange and Valve covers, Welding Curtains and Splash Shields, Safety Clothing, Equipment Covers, Flexible Connectors (Expansion Joints)

PROPERTY DATA *STYLE 8460-2-SS*

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776	34.0 oz/syd \pm 10%	1156 g/m ² \pm 10%
THICKNESS	ASTM-D-1777	0.037" \pm 0.001"	0.940 mm \pm .025 mm
TENSILE STRENGTH	ASTM-D-5034	Warp- 500 lbs/inch Fill- 400 lbs/inch	89.3 kg/cm 71.44 kg/cm
TEAR STRENGTH	ASTM-D-5587	Warp- 65 lbs. Fill- 55 lbs.	29.48 kg 24.95 kg
BURST STRENGTH	ASTM-D-3786	750 psi	52.5 kg/cm ²
FLAME RESISTANCE	FED 191/5903.2	Char Length 1/16 inch max.	0.159 cm max.
		Afterglow 1 second max.	1 second max.
		Flame Out 1 second max.	1 second max.
TEMPERATURE RESISTANCE	FED SPEC HHB-100B	-67 °F to +500 °F	-55 °C to 260 °C
BASE FABRIC and WEAVE		Fiberglass/Satin Weave	
COLOR and COATING		Silver Silicone	

DATA SHEET 13434

REV C

DATE: 2/19/99

* All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.