


ALPHA ASSOCIATES, INC.

145 LEHIGH AVE CN2013 LAKEWOOD, N.J. 08701
Phone: (732) 634-5700 Fax: (732) 634-1430

ALPHA-TEMP
STYLE P444-15A



DESCRIPTION

Alpha Style P444-15A is a two-ply laminate comprised of a fiberglass scrim and a 1.5 mil aluminum foil back.

ADVANTAGES

Aluminum surface (both sides), Excellent vapor barrier properties, Superior strength characteristics. Aesthetically pleasant appearance and broad temperature range.

APPLICATIONS

Style P444-15A is used primarily as a facing material for blanket insulation.

PROPERTY DATA *STYLE P444-15A*

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776-96	3.75oz/sy $\pm 10\%$	127.5 g/m ² $\pm 10\%$
THICKNESS	ASTM-D-1777-96	0.006" ± 0.001 "	0.152 mm $\pm 10\%$
TENSILE STRENGTH	ASTM-D-5035-95	Warp- 60 lbs./in. Fill- 50 lbs./in.	10.72 kg/cm 8.93 kg/cm
TEAR STRENGTH	ASTM-D-1424-96	Warp- 52.91 oz. Fill- 42.33 oz.	1500 gms. 1200 gms.
BEACH PUNCTURE	ASTM D-781-73	100 units (53 in/lbs)	61.0 cm/kg
FLAME RESISTANCE	FED 191/5903.2	Char Length 1/16 inch max. Afterglow 1 second max. Flame Out 1 second max.	0.159 cm max. 1 second max. 1 second max.
TEMPERATURE RESISTANCE	FED SPEC HHB-100B	-65 °F to 265 °F	54 °C to 129 °C
CORROSION RESISTANCE	FED SPEC HHB-100B	No corrosion	
PERMEABILITY: (MVTR)	ASTM E-96-94	0.02 Perms	
U.V. RESISTANCE		Not Affected	

DATA SHEET 13556

REV B

DATE: 6/21/06

* All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.