


ALPHA ASSOCIATES, INC.

145 LEHIGH AVENUE LAKEWOOD, N.J. 08701
Phone: (732) 634-5700 Fax: (732) 634-1430

ALPHA-TEMP
STYLE PPSA-44



DESCRIPTION

Alpha Style #PPSA-44 is a triple-ply laminate comprised of a white polypropylene face, a fiberglass scrim and an aluminum foil back all laminated with a flame retardant adhesive.

ADVANTAGES

Underwriters Laboratories listed, Excellent vapor barrier properties, Superior strength characteristics. Aesthetically pleasant appearance, Broad temperature range, Can be readily cleaned

PROPERTY DATA *STYLE PPSA-44*

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776	15.6 lbs./1000 SF \pm 10%	76 g/m ² \pm 10%
THICKNESS	ASTM-D-1777	0.008" \pm 0.001"	0.203 mm \pm .025 mm
TENSILE STRENGTH	ASTM-D-5035	Warp- 45 lbs./in. Fill- 45 lbs./in.	8.04 kg/cm 8.04 kg/cm
TEAR STRENGTH	ASTM-D-1424	Warp- 56.44 oz. Fill- 56.44 oz.	1600 gms. 1600 gms.
MULLEN BURST	ASTM D-3786	90 psi	6.30 kg/cm ²
BEACH PUNCTURE	ASTM D-781	150 units (39.8 in/lbs)	45.73 cm/kg
CORROSION RESISTANCE	FED SPEC HHB-100B	No corrosion	
TEMPERATURE RESISTANCE	FED SPEC HHB-100B	-65 °F to 265 °F continuous	-54 °C to 129 °C
PERMEABILITY	ASTM E-96	0.02 Perms	0.013 metric Perms

FLAME RESISTANCE: (ASTM-E-84 Tunnel)

COMPOSITE RESULTS: FLAME SPREAD = 25, SMOKE DEVELOPED = 50

SHEATHING BURN RESULTS:	POLYPROPYLENE EXPOSED	FOIL EXPOSED
FLAME SPREAD	5	0
SMOKE DEVELOPED	10	0

DATA SHEET 13336

REV F

DATE: 02/12/07

* All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.