

# ALPHA ASSOCIATES, INC.

145 LEHIGH AVENUE LAKEWOOD, N.J. 08701  
Phone: (732) 634-5700 Fax: (732) 634-1430

ALPHA - TEMP (SCRIM BASE)  
STYLE VR-R PLUS



## DESCRIPTION

POLYPROPYLENE / SCRIM / METALLIZED POLYESTER

\*THIS MATERIAL MEETS ALL CRITERIA FOR ASTM-C-1136...TYPES II & IV.

## PROPERTY DATA STYLE VR-R PLUS

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	BASIS WEIGHT	13.2 lbs/1000 sq ft +/- 10%	64.1 g/m <sup>2</sup> ± 10%
THICKNESS	ASTM-D-1777	.007" nominal	178 microns nominal
TENSILE STRENGTH	ASTM-C-1136	MD 30 lbs/inch XD 30 lbs/inch	5.25 kN/m 5.25 kN/m
ACCELERATED AGING	30 days(95% RH,120 °F)	@ 49 °C No Corrosion No Delamination	No Corrosion No Delamination
BURST STRENGTH	ASTM-D-774	100 psi	7.0 kg/cm <sup>2</sup>
BEACH PUNCTURE	ASTM-C-1136	300 Beach units (39.75 in/lbs)	8.88 Joules
LIGHT REFLECTIVITY	ASTM C-523	Result-85%	
WATER IMMERSION	24 hours @ 73°F (23°C)	No Delamination	No Delamination
PERMEABILITY (WVTR)	ASTM-E-96	0.02 Perms	1.15 ng/N's
TEMPERATURE RESISTANCE	FED SPEC HHB-100B	-40 °F to 220 °F	-40 °C to 104 °C
MOLD RESISTANCE	ASTM-C-665	No Growth	No Growth
FIRE TESTING UL 723 (CAN ULC-S102M)	COMPOSITE		
	FLAME SPREAD	25	
	SMOKE DEVELOPED	50	

DATA SHEET 13662

REV D

DATE: 9/15/09

\* All values are nominal unless otherwise specified.

### **Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications**

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.