



Alpha Maritex® Style 1200V4A-2-HT

TECHNICAL DATA

Base Fabric				Tolerance	Test Methods
Yarn					DIN 53830-3
	Warp	ET9	620 tex + V4A	± 5%	
	Weft	ET9	620 tex + V4A	± 5%	
Thread Count					DIN EN 1049-2
	Warp	12,0	1/cm	± 5%	
	Weft	6,0	1/cm	± 5%	
Weight		1.200	g/m ²	± 5%	DIN EN 12127
Weave		Panama			ISO 9354
Temperature Resistance		550°C			

Coated Fabric				Tolerance	Test Methods
Coating	coated with a grey inorganic high temperature treatment				
Weight		1.275	g/m ²	± 10%	DIN EN 12127
Thickness		1,60	mm	± 10%	DIN EN ISO 5084
Tensile Strength					DIN EN ISO 13934-1
	Warp	> 5.500	N/5cm		
	Weft	> 2.500	N/5cm		
Temperature Resistance		700°C			

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guarantee or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents.