



ALPHA

engineered composites

145 Lehigh Avenue, Lakewood, NJ 08701
T: 732.634.5700 **F:** 732.634.1430 alphainc.com

ALPHA - MARITEX
 STYLE 1500-2-SS

DESCRIPTION

Alpha Maritex Style 1500-2-SS is a fiberglass fabric impregnated with a specially formulated silicone rubber designed to meet the rigid requirements for use in nuclear reactors. This special high temperature, flame retardant silicone rubber provides greater life and improved resistance to abrasion, flexing, tearing, and puncture. Alpha Maritex Style 1500-2-SS was specifically designed as a low cost, light duty product for preparing high temperature (+500 °F) removable pads, flange and valve covers.

ADVANTAGES

Aluminum color, Water and Oil resistant, Flame retardant, Chemical resistant, Very Low Smoke, Easily sewn - drapeable, Lightweight, Easy to handle.

APPLICATIONS

Removable Insulation Pads, Flange Covers, Welding Curtains, Safety Clothing, Equipment Covers, Expansion Joints.

PROPERTY DATA
 STYLE 1500-2-SS

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>		
		<u>ENGLISH</u>		<u>METRIC</u>
WEIGHT	ASTM-D-3776	15.0 oz/sy ± 10%		510 g/m ² ± 10%
THICKNESS	ASTM-D-1777	0.014" ± 0.001"		0.356 mm ± .025 mm
TENSILE STRENGTH	ASTM-D-5035	Warp-	300 lbs./inch	53.58 kg/cm
		Fill-	225 lbs/inch	40.19 kg/cm
TEAR STRENGTH	ASTM-D-5587	Warp-	50 lbs.	22.68 kg
		Fill-	50 lbs.	22.68 kg
BURST STRENGTH	ASTM-D-3786	600 psi		42 kg/cm ²
FLAME RESISTANCE	ASTM D-6413	Char Length	1/16 inch max.	0.159 cm max.
		Afterglow	1 second max.	1 second max.
		Flame Out	1 second max.	1 second max.
TEMPERATURE RESISTANCE		Cold (-67 °F)		-55 °C to 260 °C
		Continuous 1000 hrs @ +500 °F - No Change		
		Intermittent 100 hrs @ +700 °F – Weight Loss = 10%, Strength Loss = 50%		
BASE FABRIC and WEAVE		Fiberglass/Satin Weave		
COLOR and COATING		Silver Silicone Rubber		

DATA SHEET: 13853 REV: D DATE: 10/25/17 *All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.