



ALPHA

engineered composites

145 Lehigh Avenue, Lakewood, NJ 08701
T: 732.634.5700 **F:** 732.634.1430 alphainc.com

ALPHA - MARITEX
 STYLE 1700-S MOCHA GOLD

DESCRIPTION

Alpha Maritex Style 1700-S Mocha Gold is a fiberglass fabric coated with a specially formulated dry silicone rubber. This special high temperature, flame retardant silicone rubber provides greater life and improves resistance to abrasion, tear and puncture and increases flexibility.

ADVANTAGES

Mocha Gold Color, Low Smoke, Water and Oil Resistant, Can be Easily Sewn, Flame Retardant, Chemical Resistant, Easy to Fabricate.

APPLICATIONS

Removable Insulation Blankets, Welding Curtains, Flange Covers, Expansion Joints, Equipment Covers, Safety Clothing. This product is designed specifically for high temperature (500 °F) removable blankets, and flange and valve covers where a very soft and flexible fabric is desired or needed.

PROPERTY DATA
 STYLE 1700-S MOCHA GOLD

| CHARACTERISTIC | METHOD | VALUES* | |
|------------------------|-------------|--|---|
| | | ENGLISH | METRIC |
| WEIGHT | ASTM-D-3776 | 17.5 oz/sy ± 10% | 595 g/m ² ± 10% |
| THICKNESS | ASTM-D-1777 | 0.017" ± .001" | 0.432 mm ± .025 mm |
| TENSILE STRENGTH | ASTM-D-5035 | Warp- 300 lbs/ in. Fill- 225 lbs./in | 53.58 kg/cm 40.19 kg/cm |
| TEAR STRENGTH | ASTM-D-5587 | Warp- 50 lbs. Fill- 50 lbs. | 22.68 kg 22.68 kg |
| BURST STRENGTH | ASTM-D-3786 | 600 PSI | 42 kg/cm ² |
| FLAME RESISTANCE | ASTM D-6413 | Char Length .3" max. Afterglow 1 sec. max. Flame Out 1 sec. max. | 0.762 cm max. 1 sec. max. 1 sec. max. |
| TEMPERATURE RESISTANCE | | -67 °F to +500 °F-55 °C to 260 °C | |
| BASE FABRIC and WEAVE | | Fiberglass/Satin Weave | |
| COLOR and COATING | | Mocha Gold Silicone | |

DATA SHEET: 14137 REV: B DATE: 6/04/14 *All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.