



ALPHA - ALAFLEX (SCRIM BASE)  
STYLE 2278 AMA

DESCRIPTION

Alpha Alaflex 2278 AMA is a reinforced version of 13 AM, utilizing a fire-retardant, thermo-setting adhesive, 2x2 scrim, aluminized polyester film and one layer of aluminum foil for construction.

ADVANTAGES

This product offers excellent fire-retardant characteristics and can be used as a flexible duct liner with the proper system. It offers excellent vapor barrier characteristics and high strength coupled with low cost. This product is a U.L. listed sheathing material.

PROPERTY DATA  
STYLE 2278 AMA

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776	1.6 oz/sy ± 10%	54.4 g/m <sup>2</sup> ± 10%
THICKNESS	ASTM-D-1777	0.005" ± .001"	0.127 mm ± .025 mm
TENSILE STRENGTH	ASTM-D-5035	Warp- 20 lbs./inch Fill- 20 lbs/inch	3.57 kg/cm 3.57 kg/cm
TEAR STRENGTH	ASTM-D-1424	Warp- 11.29 oz. Fill- 11.29 oz.	320 gms. 320 gms.
BEACH PUNCTURE	ASTM-C-1136	40 units (10.6 inch-lbs)	1.2 joules
FLAME RESISTANCE	ASTM D-6413	Char Length 5 inches Afterglow 5 seconds Flame Out 3 seconds	12.70 cm max. 5 seconds 3 seconds
TEMPERATURE RESISTANCE		-65 °F to 265 °F	-54 °C to 129 °C
PERMEABILITY (MVTR)	ASTM-E-96	Result = .05 Perms	
CORROSION RESISTANCE	ASTM C-1258	120 °F @95% RH 28 days Result = No Corrosion	49 °C

DATA SHEET: 13053 REV: D DATE: 01/8/15 \*All values are nominal unless otherwise specified.

**Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications**

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.