



ALPHA - WELD  
STYLE 2885

DESCRIPTION

Alpha-Weld Style 2885 (Goldengard) is a plain weave fiberglass fabric coated on one side with a fire retardant Acrylic. ANSI/FM 4950 approved for welding curtains.

APPLICATIONS

Alpha-Weld Style 2885 is designed for use in vertical welding curtains for spark containment, flash barriers and heat shields. It can also be used for protective clothing applications such as aprons, gloves, spats and gauntlets.

ADVANTAGES

The incombustible fiberglass and fire retardant coating make this fabric resistant to slag, sparks and incidental flame from cutting torches.

**PROPERTY DATA**

STYLE 2885

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776	28.0 oz/sq. yd. ± 5 %	952 g/m <sup>2</sup> ± 5%
THICKNESS	ASTM-D-1777	0.047" ± .001"	1.194 mm ± .025 mm
TENSILE STRENGTH	ASTM-D-5034	Warp- 425 lbs./inch Fill- 354 lbs/inch	75.91 kg/cm 63.22 kg/cm
TEAR STRENGTH	ASTM-D-5587	Warp- 108 lbs. Fill- 118 lbs.	48.99 kg 53.52 kg
BURST STRENGTH	ASTM-D-3786	670 psi	46.9 kg/cm <sup>2</sup>
FLAME RESISTANCE	ASTM D-6413	Char Length 1/16" max. Afterglow 6 sec. max. Flame Out 1 sec. max.	0.159 cm max. 6 sec. max. 1 sec. max.
TEMPERATURE RESISTANCE		-40 °F to +300 °F.	-40 °C to 149 °C
BASE FABRIC and WEAVE		Fiberglass/Plain Weave	
COATING		Acrylic	

DATA SHEET: 13000 FM REV: H DATE: 4/21/2017 \*All values are nominal unless otherwise specified.

**Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications**

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.