



ALPHA

engineered composites

145 Lehigh Avenue, Lakewood, NJ 08701
T: 732.634.5700 **F:** 732.634.1430 alphainc.com

ALPHA - TEMP (SCRIM BASE)
 STYLE 4313-MAE

DESCRIPTION

Alpha Style 4313-MAE is a triple ply laminate of a vinyl back with a metallized polyester film face and a fiberglass scrim tear stopper. The components are adhered together using a high performance flame retardant adhesive.

CONSTRUCTION 4 x 3 Fiberglass scrim 75G
 Clear PVC Film: 0.0008"
 Metallized Polyester Film : 0.0005"

PROPERTY DATA
 STYLE 4313-MAE

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776	2.0 oz/yd ² ± 10%	67.8 g/m ² ± 10%
THICKNESS	ASTM-D-1777	.007" ± .001"	0.178 mm ± .025 mm
TENSILE STRENGTH	ASTM-D-5035	Warp- 40 lbs/inch Fill- 30 lbs/inch	7.14 kg/cm 5.36 kg/cm
TEAR STRENGTH	ASTM-D-1424	Warp- 56.44 oz. Fill- 56.44 oz.	1600 gms. 1600 gms.
BURST STRENGTH	ASTM-D-3786	85 psi	5.95 kg/cm ²
BEACH PUNCTURE	ASTM-C-1136	150 units (39.75 inch-lbs)	4.5 joules
CORROSION RESISTANCE	AST- C-1258	106 °F @100% RH 30 days No Corrosion	41 °C
PERMEABILITY: (MVTR)	ASTM-E-96	0.02 Perms	0.013 metric Perms
WATER RESISTANCE		1 hr soak, 23 °C No Delamination	

DATA SHEET: 13956 REV: C DATE: 01/08/15 *All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.