



ALPHA - ALAFLEX  
STYLE 4313 WMS

DESCRIPTION

Alpha Alaflex Style 4313-WMS is a white vapor retardant, reinforced film with a heat sealable backing.

APPLICATIONS

This attractive, washable facing can be used to face insulation for thermal and/or acoustical applications.

ADVANTAGES

Alpha Alaflex Style 4313-WMS' heat-sealable film backing can be used to laminate the facing to most substrates with a hot roller rather than using adhesives. The resulting savings in adhesive, cleanup, and drying time makes this method of lamination cost effective.

PROPERTY DATA  
STYLE 4313 WMS

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>		
		<u>ENGLISH</u>	<u>METRIC</u>	
WEIGHT	ASTM-D-3776	2.4 oz/sy ± 5%	81.6 g/m <sup>2</sup> ± 5%	
THICKNESS	ASTM-D-1777	0.008" ± .001"	0.203 mm ± .025 mm	
TENSILE STRENGTH	ASTM-D-5035	Warp-	25 lbs/inch	4.47 kg/cm
		Fill-	25 lbs/inch	4.47 kg/cm
TEAR STRENGTH	ASTM-D-1424	Warp-	42.33 oz.	1200 gms.
		Fill-	35.27 oz.	1000 gms.
BEACH PUNCTURE	ASTM-C-1136	120 units (31.8 inch-lbs)		3.6 joules
FLAME RESISTANCE	ASTM-D-6413	Char Length	12 inch max.	30.48 cm max.
		Afterglow	5 sec. max.	5 sec. max.
		Flame Out	15 sec. max.	15 sec. max.
HEAT SEAL		4 lbs	1.81 kg	
PERMEABILITY (MVTR)	ASTM-E-96	Result - 0.01 Perms		
CORROSION RESISTANCE	ASTM-C-1258	120 °F @95% RH 28 days		49 °C
		Result - No Corrosion		
TEMPERATURE RESISTANCE		-40 °F to +200 °F		-40 °C to 93 °C

DATA SHEET: 12885 REV: D DATE: 01/08/15 \*All values are nominal unless otherwise specified.

**Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications**

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.