



ALPHA

engineered composites

145 Lehigh Avenue, Lakewood, NJ 08701
 T: 732.634.5700 F: 732.634.1430 alphainc.com

ALPHA - ALAFLEX (SCRIM BASE)
 STYLE 4348 AMA 3/10 MO

DESCRIPTION

Alpha Alaflex Style 4348 AMA 3/10 MO is a triple ply laminate made with a fiberglass scrim adhered with a fire retardant, thermo-setting adhesive to an aluminized polyester face and an aluminum foil backing. In this laminate, the aluminum of the polyester is exposed to accept sodium silicate adhesive.

1. Base Fabric - Fiberglass, 4 x 3 scrim
2. Adhesive - Fire Retardant, Thermo - Setting
3. Film - 1/2 mil polyester, aluminized
4. Foil - Aluminum 3/10 mil.

ADVANTAGES

Aluminum surface (both sides), Excellent vapor barrier.

APPLICATIONS

Flex Duct Jacketing, Refrigeration liners.

PROPERTY DATA
 STYLE 4348 AMA 3/10 MO

CHARACTERISTIC	METHOD	VALUES*	
		ENGLISH	METRIC
WEIGHT	ASTM-D-3776	1.8 oz/sy ± 10%	61 g/m ² ± 10%
THICKNESS	ASTM-D-1777	0.006" ± .001"	0.152 mm ± .025 mm
TENSILE STRENGTH	ASTM-D-5035	Warp- 30 lbs/inch Fill- 25 lbs/inch	5.36 kg/cm 4.47 kg/cm
TEAR STRENGTH	ASTM-D-1424	Warp- 14.11 oz. Fill- 14.11 oz.	400 gms. 400 gms.
BEACH PUNCTURE	ASTM-C-1136	100 units (26.5 inch-lbs)	3.0 joules
FLAME RESISTANCE	ASTM-D-6413	Char Length 2 inch max. Afterglow 2 sec. max. Flame Out 10 sec. max.	5.08 cm max. 2 sec. max. 10 sec. max.
TEMPERATURE RESISTANCE		-40°F to +300 °F	-40 °C to 149 °C
PERMEABILITY (MVTR)	ASTM-E-96	Result - .02 Perms	
CORROSION RESISTANCE	ASTM-C-1136	120 °F @95% RH 20 days Result - No Corrosion	49 °C
FLAMES SPREAD: UL-723			
		POLYESTER EXPOSED	FOIL EXPOSED
Flames Spread		15	5
Smoke Developed		15	0

DATA SHEET: 14042 REV: E DATE: 4/16/2018 *All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.