



ALPHA - ALAFLEX (SCRIM BASE)
STYLE 4348-WMMA

DESCRIPTION

Alpha Alaflex Style 4348-WMMA is a triple ply laminate made with a fiberglass scrim adhered with a fire retardant, thermo-setting adhesive to a white polyester face and an aluminized polyester backing.

1. Base Fabric - Fiberglass 4 x 3 scrim.
2. Adhesive - Fire retardant, thermo-setting white.
3. Film A - 1/2 mil. polyester aluminized.
4. Film B - polyester

ADVANTAGES

White face, excellent vapor barrier.

APPLICATIONS

Flex duct jacketing, refrigeration liners.

PROPERTY DATA
STYLE 4348-WMMA

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776	1.8 oz/sy ± 5 %	61.2 g/m ² ± 5%
THICKNESS	ASTM-D-1777	0.005" ± 0.001"	0.127 mm ± .025 mm
TENSILE STRENGTH	ASTM-D-5035	Warp- 30 lbs./inch Fill- 25 lbs/inch	5.36 kg/cm 4.47 kg/cm
TEAR STRENGTH	ASTM-D-1424	Warp- 21.16 oz. Fill- 14.11 oz.	600 gms. 400 gms.
BEACH PUNCTURE	ASTM-C-1136	150 units (39.75 inch-lbs)	4.5 joules
TEMPERATURE RESISTANCE		-40 °F to +300 °F	-40 °C to 149 °C
PERMEABILITY (MVTR)	ASTM-E-96	Result = 0.05 Perms	
CORROSION RESISTANCE	ASTM C-1258	120 °F @95% RH 28 days Result = No Corrosion	49 °C

DATA SHEET: 12857 REV: F DATE: 01/08/15 *All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.