



ALPHA

high performance fabrics & composites

ALPHA ASSOCIATES, INC. • 145 LEHIGH AVE. • LAKEWOOD, NJ 08701
T: 732.634.5700 • 800.631.5399 • F: 732.634.1430

ALPHA - WELD STYLE 6445-2-BRN

DESCRIPTION

Alpha-Weld Style 6445-2-BRN is an economy grade acrylic coated fiberglass welding curtain material. The incombustible fiberglass fabric is coated with a fire retardant red colored acrylic. ANSI/FM 4950 approved for welding curtains.

APPLICATIONS

Alpha-Weld Style 6445-2-BRN can be used for vertical welding curtains for spark and spray containment, grinding shields, arc flash barriers and fire retardant weather barrier material.

ADVANTAGES

The fire retardant red colored coating provides high visibility for safety and resistance to sparks, abrasion, water and most chemicals.

PROPERTY DATA STYLE 6445-2-BRN

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776	13 oz/sy ± 10%	442 g/m ² ± 10%
THICKNESS	ASTM-D-1777	0.0155" ± .001"	0.393 mm ± .025 mm
TENSILE STRENGTH	ASTM-D-5034	Warp- 300 lbs/in Fill- 270 lbs/inch	53.58 kg/cm 48.22 kg/cm
TEAR STRENGTH	ASTM-D-5587	Warp- 35 lbs Fill- 30 lbs	15.88 kg 13.61 kg
BURST STRENGTH	ASTM-D-3786	475 psi	33.25 kg/cm ²
FLAME RESISTANCE	FED 191/5903.2	Char Length 1 inch max. Afterglow 1 sec. max. Flame Out 0 sec. max.	2.54 cm max. 1 sec. max. 0 sec. max.
TEMPERATURE RESISTANCE FOR BASE FABRIC		0 °F to 1000 °F	-18 °C to 538 °C
TEMPERATURE RESISTANCE FOR NEOPRENE COATING		0 °F to 300 °F	-18 °C to 149 °C
BASE FABRIC and WEAVE		Fiberglass/Plain Weave	
COLOR and COATING		Red Acrylic	

DATA SHEET: 13329 FM REV: J DATE: 4/21/2017 *All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.