



ALPHA - MARITEX
STYLE 7642/9480 AMA 1S

DESCRIPTION

Alpha Style 7642/9480 AMA-1S is a lamination of fiberglass fabric to aluminum foil, using a high temperature adhesive, with a silicone wash coat to protect the exposed surface and prevent fabric fraying on the laminated edges. This composite is designed to withstand temperatures of 450°F with short exposure limits to 500°F.

APPLICATIONS

Automotive applications including insulation facings and radiant heat shields.

ADVANTAGES

High temperature resistance, reflects radiant heat, good corrosion resistance.

PROPERTY DATA

STYLE 7642/9480 AMA 1S

CHARACTERISTIC	METHOD	VALUES*	
		ENGLISH	METRIC
WEIGHT	ASTM-D-3776	10.0 oz/sy ± 10%	340 g/m ² ± 10%
THICKNESS	ASTM-D-1777	0.0011" ± .001"	0.279 mm ± .025 mm
TENSILE STRENGTH	ASTM-D-5035	Warp- 250 lbs./inch Fill- 150 lbs/inch	44.66 kg/cm 26.79 kg/cm
TEAR STRENGTH	ASTM-D-5587	Warp- 20 lbs. Fill- 20 lbs.	9.07 kg 9.07 kg
MULLEN BURST	ASTM-D-3786	200 psi	14.0 kg/cm ²
FLAME RESISTANCE	ASTM D-6413	Char Length 1/2 inch maximum Afterglow 1 second maximum Flame Out 1 second maximum	1.27 cm max. 1 second maximum 1 second maximum
TEMPERATURE RESISTANCE		-40°F to 450 °F max.	-40°C to 232 °C max.
BASE FABRIC and WEAVE		Fiberglass/Plain Weave	
COLOR and COATING		Aluminum Foil	

DATA SHEET: 14015 REV: C DATE: 1/30/15 *All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.