



ALPHA - MARITEX  
STYLE 84215/9480-AMA-1S

DESCRIPTION

Alpha Style 84215/9480-AMA-1S is a lamination of fiberglass fabric to aluminum foil, using a high temperature adhesive, with a silicone wash coat to protect the exposed surface and prevent fabric fraying on the laminated edges. This composite is designed to withstand temperatures of 450 °F with short exposure limits to 500 °F.

APPLICATIONS

Automotive applications including insulation facings and radiant heat shields.

ADVANTAGES

High temperature resistance, reflects radiant heat, good corrosion resistance.

PROPERTY DATA  
STYLE 84215/9480-AMA-1S

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>	
		<u>ENGLISH</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776	12.5 oz/sy ± 1.25	424 g/m <sup>2</sup> ± 43
THICKNESS	ASTM-D-1777	0.018" ± 0.003"	0.457 mm ± .076 mm
TENSILE STRENGTH	ASTM-D-5035	Warp- 200 lbs/inch Fill- 125 lbs/inch	35.72 kg/cm 22.33 kg/cm
TEAR STRENGTH	ASTM-D-5587	Warp- 25 lbs Fill- 25 lbs	11.34 kg 11.34 kg
MULLEN BURST	ASTM-D-3786	200 psi	14 kg/cm <sup>2</sup>
FLAME RESISTANCE	ASTM-D-6413	Char Length 1 inch max. Afterglow 12 sec. max. Flameout 5 sec. max.	2.54 cm max. 12 sec. max. 5 sec. max.
TEMPERATURE RESISTANCE		-40 °F to +450 °F	-40 °C to 232 °C
BASE FABRIC AND WEAVE		Fiberglass/Plain Weave	
COLOR AND COATING		Aluminum Foil	
BOND STRENGTH	ASTM-D-1876	30 MIN. IMMERSION (BRAKE FLUID) Result = No Delamination	

DATA SHEET: 13089 REV: D DATE: 6/24/2015 \*All values are nominal unless otherwise specified.

**Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications**

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.