



# ALPHA

engineered composites

145 Lehigh Avenue, Lakewood, NJ 08701  
**T:** 732.634.5700 **F:** 732.634.1430 alphainc.com

## ALPHALAM X 130

### Product Composition

Fluoroplastic Chemical Barrier Compound  
 100% virgin PTFE resin

### English

0.005 inch

### Metric

0.13mm

### Physical Property

### Test Method

### English

### Metric

Composite Weight, Nom

Basis Weight

7 oz/yd<sup>2</sup>

240g/m<sup>2</sup>

Composite Thickness, Nom

ASTM D1777

0.005 inch

0.13mm

Tensile Strength, Min

ASTM D4851

12 lbs/inch (MD)  
 12 lbs/inch (XD)

110 N/50mm [MD]  
 110 N/50mm [XD]

Permeation Resistance<sup>1</sup>

ASTM F739

0.0 perm

0.0 ng/N

Trapezoidal Tear Strength, Min

ASTM D4851

22 lbs/inch (MD)  
 22 lbs/inch (XD)

100 N [MD]  
 100 N [XD]

Adhesion Strength, Min

ASTM D4851

5 lbs/inch

45 N/50mm

Flexural Endurance [-1]

ASTM D4851  
 60% to 100%

75% average

Low Temperature Resistance

ASTM D1790  
 -100°F [-73°C]

Remains Flexible  
 No Delamination

High Temperature Resistance

ASTM D1790  
 +600°F [+316°C]

Remains Flexible  
 No Delamination

Water Immersion

24 hours @ 73° [23°C]

No Delamination

Mold Resistance

ASTM C665 / C1338  
 ASTM G21 [both sides]

No Growth  
 No Growth

<sup>1</sup>The AlphaLam X composite was investigated for permeation by an independent laboratory. Sulfuric acid [2N] at 5 psig was used as the test medium. The AlphaLam X composite exhibited zero breakthrough and/or permeation. Test reports available upon request.

DATA SHEET: 14184 REV. B DATE: 3/9/2016 \* All values are nominal unless otherwise specified.

**Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications**

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.