

ALPHALAM X 240					
Product Composition		Englis	<u>h</u>	<u>Metric</u>	
Fluoroplastic Chemical Barrier Compound 100% virgin PTFE resin		0.009 inch		0.24mm	
Physical Property	Test Method	English		<u>Metric</u>	
Composite Weight, Nom	Basis Weight	14 oz/yd^2		470g/m ²	
Composite Thickness, Nom	ASTM D1777	0.009 inch		0.24mm	
Tensile Strength, Min	ASTM D4851	36 lbs/inch (MD) 36 lbs/inch (XD)		324 N/50mm [MD] 324 N/50mm [XD]	
Permeation Resistance ¹	ASTM F739	0.0 perm		0.0 ng/N	
Trapezoidal Tear Strength, Min	ASTM D4851	38 lbs/inch (MD) 38 lbs/inch (XD)		170 N [MD] 170 N [XD]	
Adhesion Strength, Min	ASTM D4851	5 lbs/inch		45 N/50mm	
Flexural Endurance [-1]	ASTM D4851 60% to 100%		75% average		
Low Temperature Resistance	ASTM D1790 -100°F [-73°C]			Remains Flexible No Delamination	
High Temperature Resistance	ASTM D1790 +600°F [+316°C]			Remains Flexible No Delamination	
Water Immersion	24 hours @ 73° [23°C]		No Delamination		
Mold Resistance	ASTM C665 / C1338 ASTM G21 [both sides	5]	No Growth No Growth		

¹The AlphaLam X composite was investigated for permeation by an independent laboratory. Sulfuric acid [2N] at 5 psig was used as the test medium. The AlphaLam X composite exhibited zero breakthrough and/or permeation. Test reports available upon request.

DATA SHEET: 14185 REV. B DATE: 3/9/2016 * All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.