

EPDM Belt: Style EB 1002

Product Description: .125" Single Ply Fiberglass Inserted EPDM Belt[Press/Roto

Cured]

Rubber Polymer:

Peroxide Cured EPDM

Finished Belt Requirement

Color Black 0.125" [+/- 0.015"] Thickness, inches Width, inches *applies to roll goods 48" [+/- 0.5"] Weight, Pounds/Square yard 7.0 [+/- 0.5 lb/sqyd] Weight, Ounces/Square yard 112 [+/- 6 ozs/sqyd] Continuous Operating Temperature, F 300 Intermittent Operating Temperature, F 350 Gas Ply Thickness, Minimum Inches 0.062"

Outer Ply Thickness, Minimum Inches Rubber Compound Requirements

M6CH610A25B14 **ASTM D-2000 Elastomer Specification** Cure System Peroxide 1.12 [+/- 0.03] Specific Gravity, g/cm3 ASTM D-297 60 [+/- 5] Hardness, Durometer Shore 'A' or Equivalent **ASTM D-2240** Tensile Strength, Minimum PSI 1,450 ASTM D-412 Elongation, Minimum 300% ASTM D-412 Compression Set, Maximum¹ 25% ASTM D-412

0.062'

Dry Heat Resistance²

Weight, Change +/- 10% ASTM D-573
Hardness, Durometer Shore 'A' Change 0 to +10 ASTM D-573
Tensile Strength, Maximum Change -20% ASTM D-573
Elongation, Ultimate Minimum -30% ASTM D-573

Textile Requirements

Reinforcement Fabric Plain Weave Fiberglass
Tensile Strength, lbs/inch [Warp] 240.0

Tensile Strength, lbs/inch [Warp] 240.0 Tensile Strength , lbs/inch [Weft] 450.0

Quality Control

Certifications and test results provided with the product at the time of shipment.

DATA SHEET: 14075 REV. A DATE: 03/27/12

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.