ALPHA ASSOCIATES, INC. • 145 LEHIGH AVE. • LAKEWOOD, NJ 08701 T: 732.634.5700 • 800.631.5399 • F: 732.634.1430

# ALPHA - MARITEX STYLE FCF-1650 WHITE

## **DESCRIPTION**

Alpha Maritex Style FCF-1650 White is a fluorocarbon - impregnated and coated fiberglass fabric designed for use in removable blankets as a weather/chemical resistant barrier. This fabric is easily sewn and is flexible enough to conform to intricate shapes. The fluorocarbon impregnation and coating is extremely resistant to most industrial chemicals and has been in applications to 600° F.

### **APPLICATIONS**

Removable blankets for valves, flanges, pumps, instrumentation and freeze protection.

### **ADVANTAGES**

- -Low Flammability.
- -Good Chemical Resistance.
- -Excellent Cleanability.
- -Excellent Abrasion Resistance.
- -Minimal Smoke Levels.

#### **PROPERTY DATA**

#### STYLE FCF-1650 WHITE

CHARACTERISTIC	METHOD	<u>VALUES</u> *		
		<u>ENGLISH</u>		<u>METRIC</u>
WEIGHT	ASTM-D-3776	16.5 oz/sy ± 10%		561 g/m² ± 10%
THICKNESS	ASTM-D-1777	0.016" ± 10%		0.381 mm ± 10%
TENSILE STRENGTH	ASTM-D-5034	Warp-	410 lbs/inch	71.44 kg/cm
		Fill-	350 lbs/inch	53.58 kg/cm
MULLEN BURST	ASTM-D-3786	650 psi		45.5 kg/cm <sup>2</sup>
FLAME RESISTANCE	ASTM-D-6413	Char Length	1 inch max.	2.54 cm max.
		Afterglow	1 second max.	1 second max.
		Flame Out	1 second max.	1 second max.
TEMPERATURE RESISTANCE		-150 °F to 60	0 °F	-101 °C to 315 °C
BASE FABRIC and WEAVE		Fiberglass/Satin Weave		
COLOR		White		

DATA SHEET: 14166 REV: B DATE: 12/6/17 \*All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.