



ALPHA

engineered composites

145 Lehigh Avenue, Lakewood, NJ 08701

T: 732.634.5700 F: 732.634.1430 alphainc.com

FG-1493

(*comparable to VX-0004)

Description: Fluoroelastomer (fluorocarbon-based synthetic polymer such as 3M™ Dyneon™, Daikin DAI-EL™ and Solvay Tecnoflon®) coated Nomex® for flat cut diaphragm type applications. The combination of a fluoroelastomer coating and high temperature textile produces a coated fabric with good temperature and chemical resistance in harsh environments.

| <u>Coated Fabric Property</u> | <u>Test Method</u> | <u>Typical Results</u> |
|-------------------------------|--------------------|------------------------|
| Color | Visual | Black |
| Width | ASTM D 751 | 36" usable |
| Thickness | ASTM D 751 | .093" +/- .006" |
| Tensile Strength (W x F) | ASTM D 751 | 600 x 600 min |
| Mullen Burst | ASTM D 751 | 900 psi min |
| Adhesion | ASTM D 751 | 5 lbs min |
| Durometer (Rubber Only) | ASTM D 2240 | 75 (+/- 5) Shore A |

DATA SHEET 14251 REV. A DATE: 1/5/2017

Alpha Associates warrants the aforementioned product is free from defects in material and workmanship when used as recommended. Alpha Associates will only replace the product that is shown to our satisfaction to be defective within 30 days of delivery without charge. Defects or damage resulting from use other than recommended or misuse of any kind are not covered by this Limited Liability. These recommendations are not to be construed as warranties of any kind. Since conditions of use are beyond the control of Alpha Associates, the user assumes all risks of use. Alpha Associates will not be responsible for claims beyond the purchase value of the product. No sales representative, agent or distributor is authorized to extend any guarantee or warranty beyond the above terms. All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guarantee or warranty.

*VX-0004 is an item code used by others in the rubber industry.

*3M™ and Dyneon™ are registered trademarks of The 3M Company.

*DAI-EL™ is a registered trademark of Daikin Industries, Ltd.

*Tecnoflon® is a registered trademark of Solvay S.A.

*Nomex® is a registered trademark of E.I. du Pont de Nemours and Company.