



ALPHA

engineered composites

145 Lehigh Avenue, Lakewood, NJ 08701

T: 732.634.5700 F: 732.634.1430 alphainc.com

ALPHA – TEMP FH 6325-1 RED 36”

PRODUCT DESCRIPTION: One Side Uncured Silicone Coated Fiberglass

PRODUCT COMPOSITION [GAUGE]

Silicone Rubber – proprietary formulation

Side One –uncured silicone rubber

ENGLISH

0.010”

0.010”

Primed Fiberglass Fabric – style 162 plain weave

Interleave – polyethylene liner

0.015”

0.003”

PHYSICAL PROPERTIES

TEST METHOD

ENGLISH

Composite Weight	ASTM D3776	28.0 oz/yd ² +/- 2.0
Nominal Thickness	ASTM D1777	0.025” +/- .002”
Tensile Strength [rubber only]	ASTM D412	700 lbs/inch min
Tear Strength [rubber only]	ASTM D624	40 lbs/inch
Elongation [rubber only]	ASTM D412	300% min
Durometer	Shore A	55 +/-5
Operating Temperature		-70°F [-70°C] to +500°F [+232°C] No Delamination
Base Fabric/Weave	Style 162 fiberglass/plain	
Tensile Strength	ASTM D5035	warp 700 lbs/inch fill 420 lbs/inch
Bond Strength	ASTM D413	6.0 lbs/inch min
Color		Red Iron Oxide
Dielectric Strength		400 – 600 volts/mil
UL Recognition	UL 94 HB at 200°C	Card E201556
Product Shelf Life	75°F dry storage conditions	Six months From mfg. date
Flame Testing	ASTM D6413	25 second flame/afterglow 3.0 inch maximum char

DATA SHEET 14115 REV: B DATE: 10/01/13

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.