



ALPHA

engineered elastomers

ALPHA ASSOCIATES, INC. • 145 LEHIGH AVE. • LAKEWOOD, NJ 08701
T: 732.634.5700 • 800.631.5399 • F: 732.634.1430

Silicone Belt: Style RL 7557

Product Description:

0.250" ; 2 Ply Aramid Inserted Silicone Belt [Rotocure]

Finished Belt Requirement

Thickness, inches	0.250" [+/- 0.025"]
Width, inches <i>*applies to roll goods</i>	40 [+/- 0.5"]
Weight, Pounds/Square yard	16.0[+/- 1.0 lb/sqyd]
Weight, Ounces/Square yard	256 [+/- 16]
Roll Length (Linear Yards)	25
Pieces Per Roll (Maximum)	2
Piece Length (Minimum Linear Yards)	10
Continuous Operating Temperature, Fahrenheit	-60 to +550°
Excursion Temperature, Fahrenheit	To +600

Polymer Requirements

Polymer Content (Percent Volume)	
Gas Ply Thickness (Inches)	0.070
Outer Ply Thickness (Inches)	0.025

Standard Polymer Test Methods

Density	ASTM D-297
Tensile Strength	ASTM D-412
Elongation Strength %	ASTM D-412
Hardness	ASTM D-2240

Textile Requirements

Weight (lbs./sq.yd.)	1.2
Weight (oz/sq.yd.)	19.2
Weave Construction	Plain
Thickness (inches)	0.050
Thread Count (picks x ends)	20 x 8
Warp Tensile Strength (lbs)	325
Fill Tensile Strength (lbs)	125

Quality Control

Certifications and test results provided with the product at the time of shipment.

DATA SHEET: 14070 REV. A DATE: 03/27/12

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.