



# ALPHA

engineered composites

145 Lehigh Avenue, Lakewood, NJ 08701  
T: 732.634.5700 F: 732.634.1430 alphainc.com

## GP 60 Silicone sheet: Style WM 0118-2

### Product Description:

Commercial grade sheeting used in applications of extreme temperature. Sheeting makes excellent gasket material; offering both UV and ozone resistance.

### Product Specifications:

Thickness [mm]	3mm [+/- 0.04]
Width [mm]	1219mm [+/- 25.4]
Specific Gravity [g/m <sup>3</sup> ]	1.033 [+/- 0.03]
Roll Length [linear meters]	50
Pieces per Roll [maximum]	2
Piece Length [minimum linear meters]	10
Continuous Operating Temperature [ °C]	-60 to +230
Excursion Temperature [ °C]	to +300
Surface Finish:	Plate [smooth] or Satin [fabric]
Color:	Red Iron Oxide [others available]

### Polymer Requirements

Polymer Content [percent volume]	n/a
Durometer Shore 'A'	60 [+/- 5]
Tensile Strength, Mpa minimum	6.0
Elongation, Minimum	300%
Tear Strength [Die B], kN/m	50.0
Compression Set, 70h at 150 °C	35% Maximum

### Standard Polymer test methods

Density	ASTM D-792
Tensile Strength	ASTM D-412
Elongation Strength %	ASTM D-412
Hardness	ASTM D-2240
Tear Strength	ASTM D-624
Heat Ageing	ASTM D-573

### Heat Ageing [7h/225°C]

Durometer, max +20 Shore "A"	72 [+/- 5]
Tensile Strength , maximum -25% Mpa	-3.0%
Elongation , maximum	-10.0%

### Quality Control

Certifications and test results provided with the product at the time of shipment.

DATA SHEET 14157 REV: B DATE: 09/15/14

**Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications**

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.