



ALPHA

engineered elastomers

ALPHA ASSOCIATES, INC. • 145 LEHIGH AVE. • LAKEWOOD, NJ 08701
T: 732.634.5700 • 800.631.5399 • F: 732.634.1430

ALPHATEX 2000

<u>Product Composition</u>		<u>English</u>	<u>Metric</u>
Coated Fiberglass Substrate		0.043 inch	1.10mm
Fluoroplastic Coating Compound		15 oz/yd ²	507 g/m ²
100% virgin PTFE resin [35% to 40% by weight]			
<u>Physical Property</u>	<u>Test Method</u>	<u>English</u>	<u>Metric</u>
Composite Weight, Nom	Basis Weight	46.6 oz/yd ²	1585 g/m ²
Composite Thickness, Nom	ASTM D1777	.043 inch	1.1mm
Tensile Strength, Min	ASTM D4851	1000 lbs/inch (MD) 1000 lbs/inch (XD)	8900 N/50mm [MD] 8900 N/50mm [XD]
Trapezoidal Tear Strength, Min	ASTM D4851	50 lbs/inch (MD) 50 lbs/inch (XD)	222 N [MD] 222 N [XD]
Flexural Endurance [-1]	ASTM D4851 60% to 100%	75% average	
Low Temperature Resistance	ASTM D1790 -75°F [-60°C]	Remains Flexible No Delamination	
High Temperature Resistance	ASTM D1790 +600°F [+316°C]	Remains Flexible No Delamination	
Mold Resistance	ASTM C665 / C1338 ASTM G21 [both sides]	No Growth No Growth	

DATA SHEET: 14147 REV. A DATE: 01/01/12 * All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.