



## EPDM Belt: Style EB 1000

**Product Description:**

3.54mm"; Single Ply Wire EPDM Belt

**Rubber Polymer:**

Peroxide Cured EPDM

**Finished Belt Requirement**

Color	Black
Thickness, inches	0.125" [+/- 0.015"]
Width, inches <i>*applies to roll goods</i>	40" [+/- 0.5"]
Weight, Pounds/Square yard	8.0 [+/- 1 lb/sqyd]
Weight, Ounces/Square yard	131 [+/- 16 ozs/sqyd]
Continuous Operating Temperature, F	300
Intermittent Operating Temperature, F	350
Gas Ply Thickness, Minimum Inches	0.060"
Outer Ply Thickness, Minimum Inches	0.060"

**Rubber Compound Requirements**

Elastomer Specification	M6CH610A25B14	ASTM D-2000
Cure System	Peroxide	
Specific Gravity, g/cm <sup>3</sup>	1.12 [+/- 0.03]	ASTM D-297
Hardness, Durometer Shore 'A' or Equivalent	60 [+/- 5]	ASTM D-2240
Tensile Strength, Minimum PSI	1,450	ASTM D-412
Elongation, Minimum	300%	ASTM D-412
Compression Set, Maximum <sup>1</sup>	25%	ASTM D-412

**Dry Heat Resistance<sup>2</sup>**

Weight, Change	+/- 10%	ASTM D-573
Hardness, Durometer Shore 'A' Change	0 to +10	ASTM D-573
Tensile Strength, Maximum Change	-20%	ASTM D-573
Elongation, Ultimate Minimum	-30%	ASTM D-573

**Wire Mesh Requirements**

Weight, Pounds/Square yard	1.35
Weight, Ounces/Square yard	21.6
Tensile Strength (PSI, Minimum)	105,000
Knit (CPI)	6/8
Elongation (minimum)	25%
Thickness (Inches)	0.011

**Quality Control**

Certifications and test results provided with the product at the time of shipment.

DATA SHEET: 14073 REV. A DATE: 03/27/12

**Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications.**

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.