



ALPHA

engineered elastomers

ALPHA ASSOCIATES, INC. • 145 LEHIGH AVE. • LAKEWOOD, NJ 08701
T: 732.634.5700 • 800.631.5399 • F: 732.634.1430

ALPHA – TEMP FH 2820-6 RED 38”

PRODUCT COMPOSITION [GAUGE]		ENGLISH
Silicone Rubber – proprietary formulation		0.012”
Side One –cured silicone rubber		0.003”
Side Two – uncured silicone rubber		0.009”
Primed Fiberglass Fabric – style 7628 plain weave		0.008”
Interleave – polyethylene liner		0.003”
PHYSICAL PROPERTIES	TEST METHOD	ENGLISH
Composite Weight	ASTM D3776-96	23.0 oz/yd ² +/- 1.5
Nominal Thickness	ASTM D1777-96	0.020” +/- .002”
Tensile Strength [rubber only]	ASTM D412-92	1000 lbs/inch +/- 100
Tear Strength [rubber only]	ASTM D624	40 lbs/inch
Elongation [rubber only]	ASTM D412-92	600% +/- 60
Durometer	Shore A	45 +/-5 uncured side 55 +/-5 cured side
Low Temperature Resistance	-70°F [-70°C]	Remains Flexible No Delamination
High Temperature Resistance	+500°F [+232°C]	Remains Flexible No Delamination
Base Fabric/Weave	Style 7628 fiberglass/plain	
Tensile Strength	ASTM D5035-95	warp 250 lbs/inch Fill 200 lbs/inch
Bond Strength	ASTM D624	18 lbs/inch min
Color		Red Iron Oxide
Dielectric Strength		700 volts/mil
UL Recognition	UL 94 HB at 200°C	Card E201556
Product Shelf Life	75°F dry storage conditions	Six months From mfg. date

DATA SHEET 14110 REV: C DATE: 2/25/2015

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.