



ALPHA

engineered elastomers

ALPHA ASSOCIATES, INC. • 145 LEHIGH AVE. • LAKEWOOD, NJ 08701
T: 732.634.5700 • 800.631.5399 • F: 732.634.1430

Neoprene Belt: NB 2000

Product Description: 0.250" ; 2 Ply Fiberglass Inserted Neoprene Belt [Press Cured]

Finished Belt Requirement

Color	Black
Thickness, inches	0.250" [+/- 0.020"]
Width, inches <i>*applies to roll goods</i>	42 or 48" [+/- 0.5"]
Weight, Pounds/Square yard	15.0 [+/- 1 lb/sqyd]
Operating Temperature, Fahrenheit	220
Gas Ply Thickness, Minimum inches	0.050"
Outer Ply Thickness, Minimum inches	0.035"

Standard Polymer Test Methods (Press Cured)

Density	ASTM D-297
Tensile Strength	ASTM D-412
Elongation Strength %	ASTMD-412
Hardness	ASTMD-2240

Textile Requirements

Reinforcement Fabric	Plain Weave Fiberglass
Tensile Strength, Minimum lbs/inch [Warp]	240
Tensile Strength, Minimum lbs/inch [Weft]	450

Quality Control

Certifications and test results provided with the product at the time of shipment.

DATA SHEET # 14067 REV: A DATE: 03/27/12

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.