

ALPHA ASSOCIATES, INC. • 145 LEHIGH AVE. • LAKEWOOD, NJ 08701 T: 732.034.5700 • 800.031.5399 • F: 732.034.1430

RL 292 (AMS 3320) Silicone-Coated Pyroglas® Cloth

Alpha Associates silicone-coated Pyroglas® cloths are made from proprietary high grade silicone rubber and non-asbestos fiberglass material.

RL292 can withstand constant temperature extremes of -65° F to 450° F (-54° C to 232° C) with brief excursions to 600° F (316° C). Silicone-coated Pyroglas® cloths have excellent resistance to most chemicals and oils, and have indefinite shelf life at room temperature.

| Physical Properties | Test Method | English |
|--------------------------------------|--------------------|-------------------|
| Thickness (inches) | ASTM D1777 | 0.062" (+/-0.015) |
| | ASTM D1777 | 0.125" (+/030) |
| Width (inches) | ASTM D3774 | 48" (+/- 0.5) |
| Weight (pounds/square yard) | ASTM D3776 | 4.5 (+/5) |
| Weight (ounces/square yard) | ASTM D3776 | 72 (+/- 8) |
| Roll Length (linear yards) | | 50 |
| Pieces Per Roll (maximum) | | 2 |
| Piece Length (minimum linear yards) | | 10 |
| Continuous Operating Temperature (F) | | -60 to +500 |
| Excursion Temperature (F) | | To +600 |
| Polymer Requirements | | |
| Density | ASTM D-297 | 1.33 (+/- 0.03) |
| Tensile Strength | ASTM D-412 | 900 min |
| Elongation Strength (%) | ASTM D-412 | 400% min |
| Hardness | ASTM D-2240 | 65 (+/- 5) |
| Textile Requirements | | |
| Weight (pounds/square yard) | ASTM D3776 | 1.68 |
| Weight (ounces per square yard) | ASTM D3776 | 27.0 |
| Weave Construction | | Satin |
| Thickness (inches) | ASTM D1777 | 0.027 |
| Thread Count (picks x ends) | ASTM D3775 | 37 x 37 |
| Tensile Strength (pounds) | ASTM D5035 | 950 x 800 |

DATA SHEET: 14117 REV: D DATE: 7/21/14

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.